

Regular cement-based tile adhesive

PRODUCT

webercol fix (white) is a ready-mix cement-based tile adhesive for internal walls and floor tiling. **webercol fix (white)** is slip resistant and classified as C1T (indoor use). **webercol fix (white)** is recommended for interior tiling of porous tiles, on cement-based floors and rendered/plastered walls.

SCOPE OF USE

webercol fix (white) is used for fixing a wide range of tiles (ceramic, sandstone, etc.) on the following substrates:

- Cement and lime-based plasters/renders
- Concrete
- Screeds

CHARACTERISTICS

Appearance	Powder
Composition	Cement, silica sand and organic/inorganic additives
Color	White
Powder density	1.5
Coverage	5 to 6kg/m ²
Compressive strength	≥ 8MPa
Application Temperature:	5°C to 30°C
Mixing ratio	5 to 6 lit/25 Kg
Resting time after mixing process:	2 minutes
Pot life:	4 hours
Open time:	20 minutes
Waiting time to grouting:	24 hours
Waiting time to walk on:	24 hours
Shelf life	12 months



PACKAGING

25 Kg

TEST RESULTS

Properties	Test method	Result
Initial tensile adhesion strength	KS 2167-11	0.6 N/mm ²
Tensile adhesion strength after water immersion	KS 2167-11	0.5 N/mm ²
Open time	KS 2129-Annex	20 min

APPLICABLE STANDARDS

EN 12004:2007 - C1T (Indoor use only)
KS 2129 : 2009 ; KS 2167 : 2008

INSTRUCTIONS FOR USE

SURFACE PREPARATION

Ensure that the surface is consistent, clean and dry. Check if existing cracks are treated and/or stabilized. Check if shrinkage process is stabilized.

Ensure there are no oils and other substances that may negatively impact adhesion. Check irregularities and ensure there are no deviations higher than 5mm. If existing, regularize with tile adhesives until 10 mm thickness.

PRODUCT PREPARATION

Mix **webercol fix (white)** adding up 5 to 6 liters of clean water per 25kg bag, either manually or with a slow speed (500rpm) mechanical mixer until a uniform lump free paste is obtained. Leave the mix to rest for 2 minutes.

PRODUCT APPLICATION

Spread the mixed product on the substrate with a notched trowel, to a maximum surface area of 2m². Bed the tiles firmly unto the adhesive ensuring a good contact.

If tile sizes are larger than 900cm² (30x30cm), use the double buttering technique to ensure maximum contact between adhesive and tile.

Occasionally, remove a tile to verify good adhesion.

RECOMMENDATION

Double-butter when tile surface is larger than 900cm². It is recommended to leave a minimum of 2mm joints, filling them with **weber-joint grout**. This, to ensure release of tensions resulting from movement of the substrate.

CONSUMPTION

	Tiling Technique	
	Single buttering	Double buttering
6x6	4kg/m ²	6kg/m ²
9x9	6kg/m ²	8kg/m ²

Average values of consumption

SAFETY INSTRUCTIONS

Consult MSDS and product packaging prior to using the product.

For individual protection, it is recommended to use gloves and face masks to cover against dust.

WARNING

Freshly tiled floor using **webercol fix (white)** should not be exposed to any traffic or use in any manner for a duration of about 24 hours.

STORAGE

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of Saint-Gobain Development East Africa Ltd. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit. Performance indicated above are the result of factual knowledge. Data is resulted from normalized laboratory tests at controlled laboratory conditions.